

PRECONTRAI[®] 502

WIDTH: 180 cm	WEIGHT: 590 g/sqm
	LENGTHS*: ± 50 Im



SHADE STRUCTURE

SOLAR PROTECTION

SHADE SAILS

GUARANTEES AND LABELS




ADVANTAGES

- FERRARI[®] PRÉCONTRAI[®] TECHNOLOGY:
 - EXCEPTIONAL DIMENSIONAL STABILITY
 - HIGH LONGEVITY AND TEAR STRENGTH
- EXTREMELY UV RESISTANT
- VERY WIDE RANGE OF COLOURS
- NEW UNIQUE METALLIC COLOURS

COLOURS & REFERENCES

(COLOURS ARE INDICATIVE)



Ref. 502-2152

	Ref. 502-1013		Ref. 502-2157
	Ref. 502-1125		Ref. 502-2158
	Ref. 502-1499		Ref. 502-2159
	Ref. 502-2012		Ref. 502-2160
	Ref. 502-2135		Ref. 502-2161
	Ref. 502-2136		Ref. 502-2162
	Ref. 502-2137		Ref. 502-2163
	Ref. 502-2138		Ref. 502-2164
	Ref. 502-2141		Ref. 502-2165
	Ref. 502-2144		Ref. 502-2166
	Ref. 502-2145		Ref. 502-2167
	Ref. 502-2148		Ref. 502-2168
	Ref. 502-2149		Ref. 502-2171
	Ref. 502-2150		Ref. 502-2172
	Ref. 502-2151		Ref. 502-2173
	Ref. 502-2156		Ref. 502-8056
			Ref. 502-8102
			Ref. 502-8204
			Ref. 502-8255
			Ref. 502-8284
			Ref. 502-8341
			Ref. 502-8450
			Ref. 502-8861

TECHNICAL SPECIFICATIONS

	PRÉCONTRAI [®] 502	STANDARDS
YARN	1100 dtex PES HT	TERSUISSE
WEIGHT	590 g/sqm	EN ISO 2286-2
WIDTH	180 cm	
TENSILE STRENGTH (WARP/WEFT)	250/250 daN/5 cm	EN ISO 1421
TEAR STRENGTH (WARP/WEFT)	25/20 daN	DIN 53.363
ADHESION	9/9 daN/5 cm	EN ISO 2411
FINISH	VARNISH BOTH SIDES	
FLAME RETARDANCY	M2/NFP 92-507 • B1/DIN 4102-1 • M2/UNE 23.727 • B1/ONORM B 3800-1 • BS 7837 • CLASSE 1/UNI 9177 • LP7 • VKF 5.3/SN 198898 • G1/GOST 30244-94 • TEST 1/NFPA 701 • CSFM T19 • UBC 31-1 • CLASS A/ASTM E84 • TEST 2/CAN ULCS 109 • GROUP 1/AS/NZS 3837 • 1530.3/AS/NZS • SP METHOD 2205	
HANDLING TEMPERATURE RANGE	-30°C/+70°C	
QUALITY MANAGEMENT SYSTEM	ISO 9001	

The technical characteristics shown are average values given as a guide and may be modified. *Our packaging data are given for information only and may vary as a function of manufacturing conditions.